

Technical Characteristics

TO : PAPELES

ATT. : Controle de Qualidade

DATE : 06/06/2019

Alkaline Paper

		Minimum	Target	Maximum		
Blancura (CIE)	D65 10°	156,0	158,0	161,0	ISO-11475	C
Blancura (S/F)	ISO	96,0	98,0		ISO-2470	C
Espesor	mm	0,092	0,097	0,102	ISO-534	C
Gramage	g/m ²	72,0	75,0	78,0	ISO-536	C
Humedad	%	3,9	4,4	4,9	ISO-287	C
Opacidad	%	86,0	90,0		ISO-2471	C
Porosidad Gurley	s/100cc	7,0	10,0	14,0	TAPPI-460	C
Rigidez Longit. MD	gf.cm	1,890	2,100		ISO-2493	C
Rigidez Transv. CD	gf.cm	0,8	1,0		ISO-2493	C
Rugosidad F	mL/min	170,0	255,0	340,0	ISO-8791	C
Rugosidad T	mL/min	80,0	140,0	200,0	ISO-8791	C

Sincerely

ANTONIO CESAR F DOS SANTOS

Quality Control

PAPER - PAPEL CHAMEX 75.0

Shade

Conditioning of samples

Standard IPB

ISO 187/00

CED075 - Rev. 90 - STD