

Technical Characteristics

TO : PAPELES
 ATT. : Controle de Qualidade
 DATE : 9/3/2012

Alkaline Paper

		Minimum	Target	Maximum	
Blancura (CIE)	D65 10°	158,0	161,0	164,0	ISO-11475
Blancura (S/F)	ISO	96,0	97,0		ISO-2470
Cobb (60 Seg)	g/m ²		35,0	45,0	ISO-535
Espesor	mm	0,092	0,097	0,102	ISO-534
Gramage	g/m ²	72,0	75,0	78,0	ISO-536
Humedad	%	3,9	4,4	4,9	ISO-287
Opacidad	%	86,0	90,0		ISO-2471
Porosidad Gurley	s/100cc	7,0	10,0	14,0	TAPPI-460
Rugosidad F	mL/min	230,0	285,0	340,0	ISO-8791
Rugosidad T	mL/min	80,0	140,0	200,0	ISO-8791

Sincerely

RAFAEL RODRIGUES

Quality Control

PAPER - CHAMEX MULTI 75.0

Shade

Conditioning of samples

Standard IPB

ISO 187/00

CED075 - Rev. 83 - STD